



Protect your values.

PYRO-SAFE® FLAMMOPLAST KS 1

Intumescent fire protection coating

Description

Solvent-free and pH-neutral, halogen-free, white, aqueous, insulating dispersion for indoor use.

Application areas

- Coating for penetration sealing systems.
- Protective coating for cables and cable systems.
- Sealing of fire protection joints.



Delivery and packing

PYRO-SAFE® FLAMMOPLAST KS 1	
Packing	Pail
Container size	12.5 kg
Item number	
	01151001

Please contact us for further information:

✉ global@svt.de

Orders: order@svt.de

☎ +49 4105-40 90-0



Protect your values.

PYRO-SAFE® FLAMMOPLAST KS 1

Technical data

Field of application	Dry indoor area		
Coating	White		
Density (+20 °C)	1.20 – 1.37 g/cm ³		
Viscosity (+20 °C) [mPas]	6,000 - 10,000		
Volatile Organic Compounds (VOC)	< 50 g/l (GS-11, Green Seal Standard)		
Solid matter (weight)	62 % – 72 %		
Reaction temperature	from approx. 250 °C		
Application temperature	min. + 5 °C		
Application instructions	<ul style="list-style-type: none"> • Stir the product well before application. • The surface must be free of impurities and old coatings. • It can be applied by brush, roller or airless painting. • Application by spraying (nozzle orifice > 0.019 inch = 0.48 mm); stir with max. 2 % water addition. 		
Drying time	Dust-dry:	min. 6 hours	at +23 °C and relative humidity 65 % ± 3 %
	Can be re-applied:	min. 8 hours	
	Dried through:	min. 4 days	
Storage	Protect from frost! Store in a cool and dry place (+5 °C to +30 °C). Can be stored for at least 18 months in sealed original containers.		
Safety information	Please note our safety data sheet.		
Declaration of performance (DOP) no.	01151-PYRO-SAFE®-FLAMMOPLAST KS 1		



Protect your values.

PYRO-SAFE® FLAMMOPLAST KS 1

Applications

Penetration seal

	Certification	System name	Fire resistance class
CE	ETA-19/0228	PYRO-SAFE® Flammoplast double layer	EI 120 acc. to EN 13501-2
		PYRO-SAFE® Flammotect 4-layer	max. EI 240 acc. to EN 13501-2
DIN	Z-19.53-2400	PYRO-SAFE® Universal penetration seal COMBI 90	Fire-resistant (90 min.)
	Z-19.53-2376	PYRO-SAFE® Universal penetration seal	Fire-resistant (90 min.)
	Z-19.15-1072	PYRO-SAFE® Universal penetration seal 30	Fire-retardant (30 min.)
	Z-19.15-1903	PYRO-SAFE® Universal-V	Fire-resistant (90 min.)
	Z-19.15-1806	PYRO-SAFE® Universal-ONE	Fire-resistant (90 min.)

Joint seals

	Certification	System name	Fire resistance class
CE	ETA-13/0543	PYRO-SAFE® Joint sealing FLAMMOPLAST	EI 120 acc. to EN 13501-2

Cable coatings

	Certification	System name	Fire resistance class
DNV·GL	Certificate no.: TAE00003BM IEC 60332-3-22 Cat.A, dry film thickness > 0.5 mm	PYRO-SAFE® Cable coating FLAMMOPLAST KS 1	x

Errors, misprints and changes reserved. All of the information corresponds to the state of technology and the version of the standard that existed at the time of printing (02.2021). We will gladly provide you with information on request regarding the legal and technical framework conditions or manufacturer specifications applicable to your individual case.
© Copyright svt Unternehmensgruppe, Seevetal. PYRO-SAFE® is a registered trademark ® of the svt group, Seevetal.