



Protect your values.

PYRO-SAFE® Dekorlack SP 2

Fire protection topcoat

Description

Decorative protective coat in various RAL colours.
Yellowing resistant, quick-drying and abrasion resistant.

Application areas

- For painting over and protecting fire protection coatings against mechanical stress.
- as topcoat for PYRO-SAFE® FLAMMOPLAST SP-A2 steel coating and for PYRO-SAFE® FLAMMOPLAST KS 1 for coating concrete in dry indoor areas



Delivery and packing

PYRO-SAFE® Dekorlack SP 2	
Packing	Pail
Container size	12.5 kg
Item number	
	01153101

Please contact us for further information:

✉ global@svt.de

Orders: order@svt.de

☎ +49 4105-40 90-0





PYRO-SAFE® Dekorlack SP 2

Technical data

Field of application	Dry indoor area		
Coating	White, and other RAL colours		
Gloss level	Silky gloss		
Viscosity (+20 °C) [mPas]	2,500 - 4,500 mPas		
Volatile Organic Compounds (VOC)	< 140 g/l		
Consumption	150 g/m ² wet application yields approx. 60 µm dry film thickness.		
Application temperature	min. + 5 °C		
Application instructions	<ul style="list-style-type: none"> • Stir the product well before application. • The surface must be free of impurities and old coatings. • It can be applied by brush, roller or airless painting. • Application by spraying (airless (nozzle orifice > 0.013-0.017 inch = 0.33-0.43 mm) or compressed air (nozzle orifice ≥ 1.5-2.0 mm)). • The application of PYRO-SAFE® Topcoat SP 2 on PYRO-SAFE® FLAMMOPLAST SP-A2 or PYRO-SAFE® FLAMMOPLAST KS 1 may be started after five days at the earliest. 		
Drying time	Dust-dry:	min. 1 hours	at +23 °C and relative humidity 65 % ± 3 %
	Can be coated over with itself:	min. 6 hours	
	Dried through:	min. 4 days	
Storage	Protect from frost! Store in a cool and dry place (+5 °C – +25 °C). Can be stored for at least 18 months in the original sealed container with the option of an extension.		
Safety information	Please note our safety data sheet.		

Applications

Coating

	Certification	System name	Fire resistance class
	ETA-17/0394	Reactive fire protection coating for application on steel components	R 15 to R 60 acc. to EN 13501-2
	Z-19.51-2257	PYRO-SAFE® FLAMMOPLAST SP-A2 reactive fire protection coating acc. to ETA-17/0394	
GOST DBN / DSTU	by request	Fire protection coating PYRO-SAFE® FLAMMOPLAST SP-A2 for steel structures	R15 to R120 (according to country test standards)