

Discontinued product name: ROKU® Strip L 110

Classification E (normal flammability) according to DIN EN 13501-1
European Technical Assessment ETA-12/0152

Product Description

KERAFIX® Flexpan 200 is a flexible, intumescent material on the basis of expandable graphite, which foams with pressure when heat is applied.

Special feature:

Reliable construction material with excellent properties in standard applications.



Application Areas

- Fire protection doors of steel or aluminium
- Special application areas of fire protection doors, e. g. lock case insulations and hinges
- Safety storage cabinets, control cabinets
- In drywall construction: inspection flaps, separating wall and floor constructions
- Double floors

Technical Data

Composition:	halogen free, expanding construction material on the basis of expandable graphite
Material structure:	firm, flexible roll material
Bulk density [kg/m³]:	approx. 1100
Start of reaction [°C]:	from approx. 170
Expansion rate [x times]:	17.5 to 32 (450 °C; 30 min.; without load)
Direction of action:	three-dimensional
Expanding body:	soft, coherent mass
Expansion pressure [N/mm²]:	0.65 to 1.20 (300 °C, method 4)
Thermal conductivity [W/mK]:	0.423 (bei 10 °C)

Design Variants

KERAFIX® Flexpan 200 without additional lamination

Variant SK: single-sided adhesive

Variant DF: single-sided lamination with PVC foil in different colours

Further variants on request.

Standard colours for films and sheeting: red, black and white; more colours on request.

Supply Formats

Standard lengths: 25 000 mm and 50 000 mm

Widths: up to 320 mm

Thicknesses: 1.5 mm and 2.0 mm (special thicknesses available on request)

Special formats are available on request. The cut formats (lengths x widths) are manufactured on the basis of the general tolerance DIN ISO 2768-1-c. The formed parts and stamped parts are manufactured on the basis of the general tolerance DIN 7715-5-p2. Please observe the safety data sheet.

Note

The information in this brochure is based on our knowledge and experience to date. This information does not release the user from carrying out independent tests and trials due to the various influences when processing and applying our product. It is not possible to derive a guarantee of certain properties or suitability of the product in a concrete application case based on our information. All the descriptions, drawings, photographs, data, conditions, weights etc. included may change without previous announcement; they do not constitute the contractually agreed property of the product. The recipient of our product is responsible to observe any trademark rights and existing laws and regulations.