

# Through-penetration Firestop Systems


## System No. C-AJ-5452

### ANSI/UL1479 (ASTM E814)

F Rating — 3 Hr
T Rating — 1 – 1 1/2Hr

### CAN / ULC S115

F Rating – 3 Hr
FT Rating – 1 – 1 1/2Hr
FH Rating – 3 Hr
FTH Rating – 1 – 1 1/2Hr



System tested with a pressure differential of 2.5 Pa between the exposed and the unexposed surfaces with the higher pressure on the exposed side.

### 1. Floor or Wall Assembly

Min. 4-1/2 in. (115 mm) thick normal weight (nom. 135-150 pcf or nom. 2160-2400 kg/m<sup>3</sup>) concrete. Wall may also be constructed of any UL Classified Concrete Blocks\*. Opening shall be circular or rectangular with max diameter or dimensions of 5.1 in. (130 mm). See Concrete Blocks (CAZT) category in UL ProductIQ for names of manufacturers.

### 2. Through Penetrant

One metallic pipe or tubing to be installed either concentrically or eccentrically within the firestop system. Pipe or tubing to be rigidly supported on both sides of floor or wall assembly. The following types and sizes of metallic pipes or tubes may be used:

- A. Steel pipe — Nom 2 in. (50 mm) diam (or smaller) 0.08 in. (2 mm) (or thicker) steel pipe.
- B. Iron Pipe — Nom 2 in. (50 mm) diam (or smaller) 0.08 in. (2 mm) (or thicker) cast or ductile iron pipe.

### 3. Pipe Covering Cellular Glass Insulation

Nom 1.2 in. (30 mm) thick cellular glass units sized to the outside diam of the pipe and supplied in nom 24 in. (600 mm) long half sections. Pipe insulation installed on pipe in accordance with the manufacturer's instructions. The annular space between insulated pipe or tubing and periphery of opening shall be min 0 in. (point contact) to max 0.8 in. (20 mm). Owens Corning — FOAMGLAS One

### 4. Firestop System

The Through-Penetration Firestop System shall consist of the following:

- A. Packing Material — Min 4-1/3 in. (110 mm) thickness of min 6 pcf (100 kg/m<sup>3</sup>) mineral wool insulation firmly packed into annulus as a permanent form. Packing material to be recessed from both surfaces of floor or wall to accommodate the required thickness of fill material.
- B. Fill, Void or Cavity Material\*  
Min 0.08 in. (2 mm) thickness of fill material applied within the annulus, flush with both surfaces of floor or wall assembly.

SVT BRANDSCHUTZ VERTRIEBSGESELLSCHAFT MBH INTERNATIONAL — PYRO-SAFE FLAMMOTECT-A

\*Indicates such products shall bear the UL or cUL Certification Mark for jurisdictions employing the UL or cUL Certification (such as Canada), respectively.

Please contact us for further information:

Information: [global@svt.de](mailto:global@svt.de) Order: [order@svt.de](mailto:order@svt.de)  
+49 4105-40 90-0